



#### **Dedication**

I dedicate this book to my wife, Susan, for being the pillar that strengthens every day of my life, for helping me with the editing and for lending me family time to write this book.

#### **Special Thanks**

This book was written thanks to the motivation of friends from the plastic industry. Some of those friends and collaborators are Luis de Jesús, Carlos López, Iván Baigés, Gregorio Vélez, Runny Hernández, William Torres, Wally Cruz and Félix Colón. My friends, thank you for the collaboration and for sharing your knowledge with me.

## **Table of Contents**

rigures	
Preface	
Prologue	13
I. Introduction	1.4
What is <i>Universal Molding<sup>TM</sup></i> ?	
Fundamentals of the Injection Molding Process	
Ţ Ţ	
II. Injection Molding Process Parameters	25
Machine and Universal Parameters	
Injection Parameters	
Transfer Parameters	
Hold Parameters	29
Gate Freeze	30
Cooling Parameters	31
Recovery Parameters	33
Press Movements	35
Questions	37
III. Process Graphs	40
Molding with Graphs	
PVT Diagrams	
Questions	
IV. Plastic Morphology	
Types of Plastics	
Mechanical Properties	
Common Materials and their Characteristics	
Shrinkage	
Some Experiments	
Questions	67
V. Auxiliary Equipment	69
Material Drying	70
Extremely dry air	
Drying temperature	
Drying flow	
Drying time	
Drying equipment components	
Drying hopper	
Drying hopper size	
Drying time	
Bulk density	
Resin loader	
Dryer	
Filter	
Blower	
Desiccant hed	

Heater	
Regeneration	
Setting up drying systems	
Questions	
Blending and Material Handling	
Direct and volumetric feeder	95
Gravimetric feeder	98
Pneumatic proportional valve	100
Central blending system	101
Questions	102
Controlling the Water Temperature to the Mold	103
Material Consumption	103
Heat removed	104
Water flow	106
Estimated Cooling Time	111
Temperature Control Units (TCU)	113
TCU with direct cooling	
TCU with direct cooling and heating	
Questions	120
VI. Molding from the Desk	101
VI. Molding from the Desk	121
Press Calculations	
Clamping force fundamentals	
Projected area	
Thin wall calculation	
Forces resulting from side action mechanisms	
Three-plate molds	
Stack molds	
Platen spacing on machines with tie bars	
Platen spacing in tie-bar-less machines	
Minimum and maximum openings	
Ejector patterns	
Questions	
Injection Unit Calculations	
Injection unit size	
Nozzle tips and sprue bushings	
Fountain flow effect	
Density and specific density	
Injection speed and injection flow	
Barrel utilization	
Recovery position	
Discharge density	
Recovery speed	
Residence time	
Transfer position	
Summary	
Temperature profiles	
Procedure for measuring melt temperature	
Intensification ratio $(R_i)$	168

Machine labeling	. 169
Questions	. 170
VII. Machine Rheology	174
Plastic Melt Flow	
Shear Stress, Viscosity and Shear Rate	
Machine Rheology by Power	
Machine Rheology by Viscosity	
Approximated Rheology	
Equation to Predict Injection Time	
Questions	. 195
VIII. Determining Injection Speed	197
Laboratory I - Understanding Fill and Its Limitations, Determining Minimum	, 17,
Injection Time and Injection Pressure Limit	. 200
Laboratory II - Determination of Injection Time and Injection Speed	
Laboratory III - Rheology Graph and Determination of Ideal Injection Time and	
Speed	. 212
Laboratory IV - Approximated Graph	. 213
Laboratory V. Injection Time Prediction	. 215
Questions	. 220
IX. Verifying Fill Balance	. 222
Effect of Injection Time on Fill Balance	
Laboratory - Fill Balance	
Thermal Imbalance	
Imbalance in Molds with Cold Runners	
Questions	. 231
X. Determining Hold Stage Parameters	233
Laboratory I - Determining Hold Pressure	. 235
Verification of injected volume percentage based on the screw's position	
Laboratory II - Determining Hold Time	
Hold Stage for Molds with Hot Runners and Gate Valves	
Questions	
XI. Determining Cooling Stage Parameters	240
Understanding Your Product	
Cooling Time	
Optimization Using the Mold Temperature	
Procedure for measuring melt temperature	
Other Parameters that Affect Cooling	
How is a Cooling Experiment Organized?	
Questions	
XII. Process Limits	
What would cause the maximum injection pressure limit to be reached, and what	. 405
could be its consequences?	266
What would cause the cushion lower limit to be reached, and what could be its	. 200
consequences?	. 266

What would cause the cushion upper limit to be reached, and what could be its consequences?	267
•	207
What would cause the recovery time limit to be reached, and what could be its	267
consequences?	
What is an appropriate upper and lower limit for back pressure?	
Questions	269
Appendices	270
I - Troubleshooting	
II - <i>Universal</i> Mold Data	
III - Universal Molding <sup>TM</sup> Equations	278
IV - General Procedures for <i>Universal Molding<sup>TM</sup></i>	287
V – English Terms in Spanish	
VI - Spanish Terms in English	
VII - Operational Costs	
Bibliography	
Answers	
Index	303
Expert Opinions	

# **Figures**

I-1. Injection molding machine rheology graph	16
I-2. Conventional and approximated rheology graph	17
<i>1-3. The injection stage</i>	19
I-4. The spaces that the plastic occupies in the mold	20
I-5. The check ring	
I-6. Position of the check ring during recovery	
I-7. The recovery stage	
II-1. The injection stage	27
II-2. Walls with cold molds and extended cooling times	
II-2a. Walls with hot molds and shortened cooling times	
II-3. Backpressure	
II-4. Decompression	
III-1. Graph of ideal injection	
III-2. Control zone graph of injection speed or flow	
III-3. Graph of hold zone or pressure control	
III-4. Graph of recovery zone	
III-5. Graph with limited pressure	
III-6. Graph illustrating premature transfer	
III-7. Graph illustrating cushion equal to zero	
III-8. Graph illustrating unachieved programmed injection speed	
III-9. PVT (Pressure, Specific Volume and Temperature) diagram	
III-10. PVT diagram with molding stages	
IV-1. Illustration representing amorphous and semi-crystalline molecular organization	51 zation
1v-1. Itustration representing amorphous and semi-crystatine motecular organi.	
IV 2. Graph illustrating stiffness versus temperature in amorphous materials	
IV-3. Graph illustrating stiffness versus temperature in semi-crystalline materials	
IV-4. Overlaid graphs of stiffness versus temperature of semi-crystalline and amorphisms.	
materials	
IV-5. Common amorphous amd semi-crystalline materials	
IV-6. List of mechanical characteristics of amorphous and semi-crystalline materia	
IV-7. List of process characteristics of amorphous and semi-crystalline materials	
IV-8. Amorphous material shrinkage	
IV-9. Semi-crystalline material shrinkage	
IV-10. The effect of hold time on the part weight in amorphous and semi-crystr	
materials	anne 62
IV-11. The effect of hold pressure on the part weight of amorphous and semi-crystr	
materials	
IV-12. The effect of injection pressure on injection time with amorphous and	
crystralline materials	
V-1. The mechanics of drying thermoplastics	
V-2. Drying hopper and dryer	
V-3. Drying hopper V-4. Volume/residence time	
V-5. Drying circuit	
V-6. Regeneration stage	
V-7. Portable unit	84

V-8. Hopper above the extruder	
V-9. Integrated unit	
V-10. Central drying system	
V-11. Table of materials and their drying parameters	87
V-12. Table of materials and their bulk densities	89
V-13. Dry air flow required for each lb/hr of material consumption	91
V-14. Additive feeder	96
V-15. Graph of speed adjustment vs. feeding rate	
V-16. Two feeders mounted in one system	
V-17. Gravimetric system	
V-18. Pneumatic proportional valve	100
V-19. Central blending system	
V-20. Table of energy required for some materials	104
V-21. Table of thermal load of some materials	105
V-22. Water flow through the mold and Delta T	
V-23. Water hoses connected to the mold in series and in parallel	
V-24. Temperature between cavities	
V-25. Table of constants for cooling time equation	
V-26. Inlet and outlet water temperature and pressure	
V-27. Diagram of direct cooling components	
V-28. Diagram of direct cooling and heating components	
V-29. Three machines sharing a chiller	110 110
V-30. Three machines sharing a chiller, with a stopped machine	119
VI-1. Table of pressure factors for some materials	123
VI-2. Projected area of a sphere	124
VI-3. Projected area of a cube	
VI-4. Projected area of a cup	
VI-5. Nylon spools and runners with and without parts	
VI-6. Projected area of one of the 12 spools and its runner	
VI-7. Area of the runner	
VI-8. Example of an L-shaped part	
VI-9. Flow path of a spool	
VI-10. Thickness (T)	
VI-11. Table of thin wall criteria	
VI-12. Linear interpolation of the pressure factor	
VI-13. Side action mechanisms (sliders) driven by clamping force	
VI-14. Measurements to calculate the projected area	
VI-15. Lateral force per slider	
VI-16. Resulting force	
VI-17. Three-plate mold	136
VI-18. Stack mold	137
VI-19. Stack mold force vectors	137
VI-20. Platen spaces with tie bars	138
VI-21. Platen spaces on tie-bar-less machines	139
VI-22. Minimum press opening	
VI-23. Maximum press opening	
VI-24. Ejector pattern	
VI-25. Maximum recovery	
VI-26. The nozzle tip and sprue bushing	

VI-27. Diameters and radii of the nozzle tip and sprue bushing	145
VI-28. Defect caused by stress concentration at the edge of the nozzle	
VI-29. Defect caused by a sprue stuck in the nozzle	147
VI-30. Another defect caused by a sprue stuck in the nozzle	147
VI-31. Thermoplastic melt flow in a mold	148
VI-32. The fountain flow effect	149
VI-33. Example of fountain flow effect using a piece of napkin	149
VI-34. Fill positions	
VI-35. Residence volume	
VI-36. Table showing example of residence T <sub>r</sub>	159
VI-37. Table of residence time, according to % of utilization	160
VI-38. Table showing % of utilization according to industry type	
VI-39. Transfer position	
VI-40. Tables showing transfer position criteria	
VI-41. Screw positions	
VI-42. The barrel's heat zones	
VI-43. Temperature profiles	
VI-44. Intensification ratio	
VII-1. Orientation of molecules in a melt flow	
VII-2. Shear stress	
VII-3. Half of the melt flow	
VII-4. Velocity vectors in a melt flow	
VII-5. Newtonian and pseudoplastic melt flow	
VII-6. Graph of machine rheology by power	
VII-7. Graph of injection time versus peak power	
VII-8. Zone where the change in injection time is minimal or where the power s	
contributing	
VII-9. Zone where the change in relative viscosity is minimal	
VII-10. Readings of transfer pressure and injection time	
VII-10. Readings of transfer pressure and injection time	
VII-12. Graph of linear behavior between relative viscosity and injection time	
VII-13. Example of injection times and transfer pressures	
VII-14. Examples of rheology values	
VII-15. Graph of the linear effect between average injection flow and peak power.	
VII-16. Graph of the linear effect between relative viscosity and injection time	
VII-17. Table including 8 equidistant injection times	
VII-18. Graph of approximated rheology by power	
VII-19. Graph of approximated rheology using relative viscosity and shear rate	
VII-20. Superimposed graphs of complete and approximated reology	
VII-21. Graph of standardized rheology in %	
VII-22. Injection time for conventional molding industries	
VII-23. Injection time for industries that mold friction-sensitive materials	
VII-24. Injection time for high-volume injection industries	
VIII-1. Flow chart of Universal Molding <sup>TM</sup> events	
VIII-2. Tables to select the injection-to-hold transfer position	
VIII-3. Determination of minimum injection time and maximum injection p	
(example)	
VIII-4. Effect of injection time on parts fill	
VIII-5. Rheology table headers	208

VIII-6. Table of approximated rheology by power	209
VIII-7. Table showing conventional rheology by power	210
VIII-8. Example of a table and graph of conventional rheology by power	
VIII-9. Example of a table of approximated rheology by power	
VIII-10. Graph with linear equation between peak power and average injection flow	
VIII-11. Table and graph of approximated rheology by power	
VIII-12. Table of approximated rheology by power	
VIII-13. Rheology graph indicating injection times by industry type	
IX-1. Multi-cavity mold with unbalanced fill	
IX-2. Graph of the effect of injection speed on the fill of incomplete parts	
IX-3. Fast and slow fill	
IX-4. Example of flow sequence of the runner	225
IX-5. Example of slow fill	
IX-6. Example of fast fill	
IX-7. Example of incomplete fill	
IX-8. Parts separated from the runner	
IX-9. Table with incomplete cavity weights and corresponding fill deviations	228
IX-10. Column plot with % of cavity fill deviation	
X-1. Graph of the effect of hold pressure on the weight of the parts	
X-2. Extended cooling time	
X-3. Table of the effect of hold pressure on the weight of the parts	
X-4. Graph of the effect of hold pressure on the weight of the parts	
X-5. Graph indicating hold pressure range	
X-6. Determination of hold pressure with the cushion's position	238
X-7. Graph indicating excessive hold pressure	
X-8. Correction when cushion is zero	
X-9. Extended cooling time	242
X-10. Table of the weight of the parts and their respective hold and cooling times	243
X-11. Graph of the effect of hold time on the weight of the parts	
X-12. Mechanical characteristics of materials which should be considered during	
XI-1. Mold temperature optimization experiment table	253
XI-2. Example of parts of a two-cavity mold	
XI-3. Table with effects of mold temperature on critical measurement	
XI-4. Graph of mold temperature effect on critical measurements	
XI-5. Graph showing linear equations using temperatures and measurements of a	
cavity mold	
XI-6. Table with temperature limits at critical measurements of two parts	
XI-7. Table of cooling parameters (temperature and time), with their combinations	
their repetitions	

#### **Preface**

Injection molding was, for many years, a space occupied by the experienced masters of the plastics industry. Fortunately, today there are several techniques that accelerate learning and mastery of injection molding.

We have experimented with numerous molders of all calibers. Among us we have never found two that use identical molding techniques. Not only are the molding techniques different, but language, order of execution, definitions, parameter usage, equipment identification, procedures, and communication are not equal. These are the reasons that motivate the writing of this book.

Universal Molding<sup>TM</sup> (abbreviated  $MU^{TM}$ ) aims to unify molding styles, use valid process definitions, use Universal language, and standardize clear and representative procedures for all stages of injection molding.

This book is not limited to just newcomers to the industry; it is also recommended for experienced molders who wish to standardize and increase the number of competent molders in their sector. Universal Molding  $^{TM}$ : Systematic Injection Molding Optimization Method ( $MU^{TM}$ ) is for anyone who wants to learn systematically and effectively about injection molding.  $MU^{TM}$  guides the molder to determine the Universal parameters characteristic of the mold, regardless of the injection machine used. There is a concern that affects a minority in the plastic industry, artificial intelligence. We see it as a tool that will help address the lack of and empirical approaches standardization in process optimization. The integration of artificial intelligence in  $MU^{TM}$  considers the fundamental principles of standardization, rapid learning, efficient processes, and significant benefits. We must all strive to improve, accept, and learn new methodologies and technologies that strengthen continuous growth.

### **Prologue**

What is the definition of an "optimal" injection polymer molding process? In reality, we do not establish an optimal process, but instead define an optimal operational window around the values of certain molding parameters that an optimization laboratory leads us to establish and define as 'nominal'. Using the tools provided by the internet we can find countless definitions and/or methods on what is an optimal process, how to establish it, and even how to monitor it. These definitions, in short, establish that an optimal polymer molding process is "the result of a particular combination of molding parameter values... inside an operational window... able to consistently produce a plastic part that meets all cosmetic, dimensional and functional design requirements... in the shortest machine time possible." This, for any combination of raw material, mold design and molding cell (i.e. injection machine, dryer, temperature controls, etc.). Similarly, that optimal process cannot be if it goes against the ability of the mold, or even the molding machine, in order to repeat the same cycle of behavior infinitely.

The author of the book has devoted much of his professional life to systematically identifying two things. First, how to establish that optimal operational window in a molding process; and second, how to make that optimal process window for any combination of raw material, mold and molding equipment the same regardless of who runs it or where the optimization lab is performed. That is why "Universal" is in the title of this book. It is the intention of the author, with the tools presented in this, his book, to make the Process Engineer able to identify the minimum requirements with which each of the equipment and utilities that make up the molding cell must meet. Once the equipment is successfully selected, it provides the tools for the selected equipment to become the foundation on which, in a complete way, the Process Engineer can develop the laboratory and establish the design experiments that will shape that combination of 'nominal' parameters around which will define the limits of that optimal operation window being validated. This....in the shortest machine time possible.

Felix Colón Ortiz Injection Molding Process & Tooling Engineering Professional

# I. Introduction

- What is *Universal Molding*<sup>TM</sup>  $(MU^{TM})$ ?
- Fundamentals of the Injection Molding Process

In this section we want the readers to familiarize themselves with the terminology, emphasizing those parameters that are most significant to the process and establishing the language used in this book.

## What is *Universal Molding*<sup>TM</sup>?

*Universal Molding*<sup>TM</sup>  $(MU^{TM})$  is an injection molding process optimization discipline. It was developed with the collaboration of the Caribbean plastic industry and the academia (professor and students) from the University of Puerto Rico, Mayagüez Campus (UPR RUM).

**MU**<sup>TM</sup> is a *discipline* that emphasizes the maximization of resources and focuses on the quality of the product, utilizing process optimization methods proven by means of organized and scientifically backed molding techniques. This tecno-scientific background increases efficiency, decreases product cost, and shortens manufacturing cycles.

**MU**<sup>TM</sup> is a *common language* used by molders to eliminate terminology confusion. The equipment is labelled with a language that represents their capacities. It is this language of *Universal* process parameters that simplifies the transference of processes between machines. It is a language that defines a product and its utilization.

MU<sup>TM</sup> is an *organizing committee* (or *Universal* committee). It is a chosen group that promotes that discipline. It is a *Universal* committee represented by all departments of the *Universal* factory. It is represented by the Production, Quality Control, Equipment Maintenance, Mold Maintenance, Engineering and Sales departments.

*MU*<sup>TM</sup> is an *endless discipline* that never ceases to grow or improve. The *Universal* committee has the responsibility to evaluate and unanimously adopt procedures that improve the existing ones.


**MU**<sup>TM</sup> is based on precise and representative process procedures. At each stage, a procedure is followed to determine the parameters, either through linear equations or, in many cases, with a nonlinear component generated by artificial intelligence (AI).

 $MU^{TM}$  is maximizing the utilization of the machinery. It is determining the appropriate equipment and its optimal process parameters.

Some of the techniques used are:

1- Injection machine rheology. This is an effective, proven technique used to determine injection time. Using a graph, it shows the effect of the injection time versus energy per unit of volume.

In the following graph, the area below the curve demonstrates the percentage of energy consumed for each decrement in injection time.




#### I-1. Injection molding machine rheology graph

Note that the power consumption increases as the injection time decreases. This graph shows that the power required at higher injection rates is considerably high, or the power consumed by the injection unit is more significant at lower injection times. The idea is to select an injection time in the zone in which the time stops contributing with an increase in power.

Later we will explain how to develop and utilize this injection molding rheology graph.

2- Approximated rheology. Developing a rheology laboratory with an injection machine consumes time and resources. With approximated rheology, a mathematical prediction technique, the laboratory can be achieved in less than a third of the time.

The following graph of injection time versus power by volume compares the two methods: conventional machine rheology and the approximated method.



#### *I-2.* Conventional and approximated rheology graph

Both methods conceptually function in the same way. The difference is that using the approximated method consumes less time and resources.

Again, the development of these graphs will be explained in later chapters.

## **Fundamentals of the Injection Molding Process**

The basic stages of the injection molding process are:

- injection
- changeover or transfer
- hold
- gate freeze
- cooling
- recovery


Each stage has a function and a specific result. Understand each one of these stages thoroughly since their descriptions will be continually referenced. **Injection** - In this stage the mold cavities and runner are filled close to 95% of their total volume, and the screw acts like a piston that transfers melt from the injection unit to the mold. Here is where you program a velocity or injection flow rate that guarantees the best melt properties. These properties could be parts without burns, no flowlines, no degradation, minimal stress concentration, etc. When the hot melt enters the mold, it is met with cold walls and rapidly densifies until it solidifies. The slow fill increases densification or viscosity and, consequently, it could make filling the mold difficult and may even cause the melt to solidify prematurely before the mold has been filled. In this stage the injection time, as well as the injection pressure, are results and not control parameters. Do not confuse these with *injection pressure limit* or with *injection time limit*, which are limits that are programmed to protect the tooling and the equipment. This stage is known as the injection speed control stage.

**Transfer** (**changeover**) – This is what determines the end of the injection stage. Once the injection unit has filled the mold **close to 95%**, the injection stage ends, and the hold stage begins. The injection unit comes with a linear encoder that measures the injection screw displacement, which is how the injection unit knows when the melt is close to filling 95% of the mold. Avoid trying to fill the mold 100% in the injection stage. Let's see some of the reasons why:

- It could cause flash on the molded parts. What stops the screw is the melt in front of the injection unit; trying to stop at exactly 100% without opening the mold would be difficult.
- At a high speed, trying to fill a mold to 100% could create a bounceback effect on the screw. Plastic melt is compressible and during injection it is placed under pressure. This pressurized melt can act like a compressed spring, pushing the injection backwards and causing a suckback effect that pulls back part of the melt that was injected.
- Another reason that it should not be done is because of material shrinkage. Melt occupies more space than solidified material. Once the melt enters the mold it will cool, gradually shrinking and leaving space for more material.

Note: Some molds present an extreme difficulty in filling, for example, nylon ties which are long and thin, or micro-molding applications with

narrow and awkward spaces for filling. In these cases, a filling percentage higher than 95% may be required.




#### I-3. The injection stage

**Hold** - In this stage the screw continues to move like a piston, forcing more melt into the cavities until it fills the portion that was not filled in the injection stage. Without opening the mold, the injection unit compresses the melt, packing more material into the mold until the cavities are completely filled. Here the molder adjusts the compacting pressure.

During this stage we achieve the proper weight for the molded parts, or what we *Universal* Molders call *mass dimensions*. The mass dimensions are those that are a function only of the quantity of material and should not be confused with the dimensions that are due to the effect of material shrinkage. Shrinkage is controlled during the cooling stage. As indicated previously, during the hold stage we only control the mass dimensions, the dimensions that are a function of the quantity of material.

Gate Freeze – During the hold stage, the parts are pressurized until the material in the gates solidifies, creating a seal that keeps the melt inside the cavities. Let's look at the spaces that the plastic occupies in the mold.



I-4. The spaces that the plastic occupies in the mold


A gate is a small opening through which the melt enters the cavities. The melt enters the mold through a sprue and travels through the runner until it reaches the cavity gates. The melt is forced through the narrow openings of the gates until the cavities are filled. The plastic is held inside the cavities until the gates solidify. It is important to understand:

- If you remove the hold pressure prematurely, the melt will return to the runner and even to the injection unit.
- If the hold time is more than required, the molder will end up "molding runners".

In some molds with hot runners, the melt never solidifies and is integrated as part of the filling for the next parts. The goal of this type of mold is to reduce the waste of material from the sprue. However, even in this case, the gates on the cavities must solidify before releasing the hold pressure.

In other molds, in addition to having hot runners, valves are integrated into the gates. These gate valves remain open during filling and close once the holding is complete.

The screw acts as a piston thanks to the check ring that floats between the screw and the screw tip. During injection, this check ring moves against the screw, creating a seal and keeping the melt from returning to the screw.



#### I-5. The check ring

During injection, the pressure in front of the check ring is greater than the pressure on the screw side, causing the check ring to move against the screw to create a seal.

There exist some screws that do not have a check ring. Rigid PVC material is very sensitive to the friction of the melt against the check ring, and it is common to see that this type of system does not use any check ring. Instead, these screws come equipped with an anti-rotation mechanism so that they will not turn as a consequence of excessive melt pressure.


**Cooling** – In this stage, heat is removed from the parts, until they can be easily demolded with acceptable thermal dimensions. Thermal dimensions are dimensions that are a function of shrinkage and not of the quantity of packed mass. The molecules of thermoplastic melt are in continuous movement; as they cool, they look for conformity and accommodate themselves to occupy less space. The objective is to paralyze the molecular activity and manipulate this shrinkage to our advantage.

#### This means:

- Cold molds and extended cooling times result in parts with thicker walls.
- Hot molds and short cooling times result in parts with thinner walls.

Thermal dimensions and some mechanical properties are a function of how quickly the heat is being removed from the parts. These mechanical properties could include rigidity, translucence, crystallinity, etc. Later on, we will explain how thermal dimensions are a function of cooling time and mold temperature.

**Recovery** - In this stage, the screw reloads material for the next shot. The main goal of this stage is to produce a homogeneous melt. During recovery the check ring moves away from the screw, which allows the melt to flow to the front of the screw as the screw turns.



#### *I-6. Position of the check ring during recovery*

The melt that accumulates in front of the screw is what pushes the screw backwards.

Recovery occurs at the same time as the cooling stage. Under normal circumstances recovery ends before the cooling stage ends and, if the


cooling stage ends first, permission to open the mold is denied by the machine's controls. Under these circumstances, where the permission to open the mold has been denied and if no alarms exit that would cause the process to stop, the cooling time will be extended, altering the thermal dimensions.

Imagine what would happen if the mold opened during the recovery stage. The melt would drool into the mold. During recovery, the plastic is pressurized and the mechanism that holds the melt in place is the filled mold. As a rule, recovery should end close to a second before cooling. Permission to open the mold during recovery can only occur if the injection unit has been equipped with a valve on the nozzle.

It is important to know that the injection unit utilizes two sources of heat to melt the plastic: the heating bands on the barrel and friction. Generally, 50% of the heat comes from the heater bands and the remaining 50% comes from the friction of the plastic moving inside the barrel.

Later we will discuss in more detail the parameters that govern recovery, which are recovery speed, recovery position, backpressure, decompression and melt temperature.

**Mold Movement** – During this stage we demold the parts. Once the cooling stage has ended, the sequence is: the mold opens, if cores exist they will disarm in order to liberate the parts, the parts are ejected, the cores are relocated into the mold, the mold begins to close, the mold protection system is activated and, if the mold protection does not detect any issues, the injection machine reaches full closure force, and a new cycle begins.



check ring moves, allowing the flow of melt. That melt accumulation in the front is responsible for pushing the screw backwards. The backpressure opposes the free In the recovery stage the screw rotates, moving the melt to the front of the barrel. The movement of the screw, resulting in shear friction on the material, which, in turn, generates heat and contributes to the melting process.

## I-7. The recovery stage